



PERMANENT CROSS-ROAD OR LONGITUDINAL PATCH DETAIL

-FULL DEPTH **SAW CUT** 9'-0" PLUS OUTSIDE DIAMETER OF PIPE (MIN.) LONGITUDINAL: FULL WIDTH OF LANE(S) DISTURBED -FULL DEPTH **SAW CUT** PLACE HOT MIX TO THE TOP OF THE EXISTING ROADWAY. USE 2" TYPE 'C' HOT MIX ON VARIABLE DEPTH BCBC OVER PCC PATCH. **EXISTING 1**'-0" **1'-0"**► -8" MIN PCC PATCH **PAVEMENT** 2'-0 2'-0" BACKFILL BORROW TYPE C PLACED IN 8" LIFTS LOOSE MEASUREMENT AND COMPACTED PER DELDOT **SPECIFICATIONS** INSTALL PIPE IN ACCORDANCE WITH SECTION 601. SEE D-8 FOR PIPE BEDDING PIPE O.D. 18" MIN _

NOTES:

- 1). PATCH WIDTHS ARE MEASURED ALONG THE ROADWAY CENTERLINE. CONSTRUCT PATCHES THE FULL WIDTH OF THE LANE OR LANES DISTURBED.
- 2). THIS IS A MINIMUM PATCH. IF THE EXISTING ROADWAY HAS A HEAVIER CROSS SECTION THAN SHOWN HERE, IT WILL BE REPLACED WITH THAT CROSS SECTION, OR AS DIRECTED BY THE ENGINEER.

PERMANENT CROSS-ROAD OR LONGITUDINAL PATCH DETAIL * EXISTING CONCRETE PAVEMENT OVERLAYED WITH HOTMIX LOCATIONS

PERMANENT CROSS-ROAD PATCH OVER PIPE TRENCH

RECOMMENDED

PERMANENT CROSS-ROAD PATCH OVER PIPE TRENCH

STANDARD NO. P-4 (2024)

SHT. 1 OF 1 APPROVED

DEPUTY DIRECTOR - DESIGN

CHIEF ENGINEER

01/11/2024 DATE

22 December 2023

22-DEC-2023